



Fire sleeve - F 88 PYC

The flat coated fire sleeve with polychloroprene and high material density.

Certifications

DIN 5510-2:1999 + ISO 5659 Toxi
ISO 15540:1999 NW20
Type Approval GL (Germanischer Lloyd)

Technical data

Backing material ISO 2078 mineral fibre
Coating PYC

Temperature Range continuous temperature: -40 to +260 °C
short-term 800 °C

Technische Werte wall thickness: 2,5 - 3,0 mm; weight: 2,8 kg/m²; REACH: complies
Available sizes DN14 – DN140; available lengths 25 m; 50 m on request

Product details

DN	product number	approx. weight g/m
14	4418 8 014	212
16	4418 8 016	215
18	4418 8 018	234
20	4418 8 020	245
22	4418 8 022	256
24	4418 8 024	266
26	4418 8 026	278
28	4418 8 028	290
30	4418 8 030	301
32	4418 8 032	314
36	4418 8 036	328
38	4418 8 038	340
40	4418 8 040	353
42	4418 8 042	371
45	4418 8 045	387
48	4418 8 048	408

DN	product number	approx. weight g/m
50	4418 8 050	442
52	4418 8 052	453
55	4418 8 055	464
60	4418 8 060	488
65	4418 8 065	578
70	4418 8 070	630
75	4418 8 075	650
80	4418 8 080	684
85	4418 8 085	755
90	4418 8 090	800
100	4418 8 100	860
110	4418 8 110	890
120	4418 8 120	920
125	4418 8 125	978
140	4418 8 140	983